



Carrington Specialty Products' Neoprene-blend material (4116) meets the following "self-extinguishing" flammability spec:

UL94HF-1

UL94 is a horizontal burn test requiring 2" x 6" specimens. A Bunsen burner is applied to the material for 60 seconds and then removed from the specimen.

A material classified 94HF-1 shall:

- A) not have more than one specimen out of each set of five specimens continue to flame for more than 2 seconds after the test flame has been removed.
However, this one specimen shall not flame for more than 10 seconds.
- B) not have any test specimens affected for a distance greater than 2.25 inches from the end exposed to the test flame.
- C) not have any of the specimens drip flaming particles which ignite dry absorbent surgical cotton placed 12 inches below the specimen.